



TESTING MATERIALS

Please find enclosed :

- 1 Nitrile Drum Seal (Red)
- 1 EPDM Drum Seal (Blue)
- 1 Viton Drum Seal (Green)
- 1 Santoprene (Black)

Westcott Distribution Inc. is pleased to send this material to you for testing purposes. We will also appreciate a report back from you.

Please weigh each piece prior to test. Then put all materials in an non-reactive container, with the fluid to be tested. The container must be tightly sealed for the duration of the test to reduce the risk of spillage. Leave the test materials for 48 hours in the solution, remove from solution, weigh each piece again and then visually inspect each piece. Look for cracks, swelling, discoloration, softening, etc.

After testing, please wash all materials off with an appropriate neutralizing agent. If the damage to the seal is simply swelling, place the seal in the sun for a couple of hours to degass it and it should be ready to be reused for testing again.

Please fill out the report below and return to Salesman or Westcott Distribution, Inc.

Westcott
Distribution

184 West Tenth Street, New York, 10014
Voice (646) 486 3636 Fax (212) 243 6070

10/23/03



Company Name _____

Address _____

Phone _____

Test Conducted by _____

Fluid _____ Concentration _____

Temperature _____ Dates of Test _____

Item	Weight Before	Weight After	Visible Changes
Red Seal			
Blue Seal			
Green Seal			
Black Seal			