

Material Temperature (°F)	PVC 70/140	PUR 70/140	PE 70/140	EVA 70	Material Temperature (°F)	PVC 70/140	PUR 70/140	PE 70/140	EVA 70
Tin Chloride	E E	E E	- -	-	Whiskey	E E	G U	E E	E U
Titanium Tetrachloride	E U	L U	- -	-	White Gasoline	E E	E G	U U	U
Toluol or Toluene	U U	L U	U U	U	White Liquor (Paper Industry)	E E	- -	- -	-
Tributyl Phosphate	U U	- -	U U	U	Wines	E E	- -	E E	G
Trichloroethylene	U U	L U	L L	L	Xylene or Xylo	U U	G L	U U	L
Tricresylphosphate	U U	U U	L L	L	Zinc Chloride	E E	E E	E E	E
Triethanolamine	G U	- -	G L	L	Zinc Chromate	E E	E E	E E	E
Triethylamine	G L	- -	- -	-	Zinc Cyanide	E E	E E	E E	E
Trimethyl Propane	L U	- -	- -	-	Zinc Nitrate	E E	E E	E E	E
Trisodium Phosphate	E E	E E	E E	E	Zinc Sulfate	E E	E E	E E	E
Turpentine	L U	E G	L U	U	Mixtures of Acids				
Urea	E E	E E	E E	E	Nitric 15 Pct.				
Urine	E E	E E	E E	E	Hydrofluoric 4 Pct.				
Vinegar	E G	G L	E G	E	Sodium Dichromate				
Vinyl Acetate	U U	U U	L U	U	13 Pct.				
Water—Acid Mine Water	E E	G U	E E	E	Nitric Acid 16 Pct.				
Water—Distilled	E E	G U	E E	E	Water 71 Pct.				
Water—Fresh	E E	G U	E E	E					
Water—Salt	E E	G U	E E	E					

REHAU®

North American Headquarters & Technical Center
 P.O. Box 1706, 1501 Edwards Ferry Road
 Leesburg, Virginia 22075
 Toll Free 1-800-247-9445
 (703) 777-5255 • Telex 89-621 • Telefax (703) 777-3053

Important Notice: The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. Before using, the user shall determine the suitability of the information for user's intended use and shall assume all risk and liability in connection therewith. **REHAU DISCLAIMS ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE.**